



REPREVE



COMMERCIAL - TECHNICAL DATA / Tecnologia



CANOA ACTIVE ECO

81% RECYCLED POLYESTER
19% LYCRA XTRALIFE

| Test Method for Knit Fabrics | | STANDARD (estandar) | |
|---|---------------------|---------------------|------------|
| Width / Ancho NTC 228-2011 | | In | Cms |
| | | 61 | 155 |
| Weight / Peso ASTM D 3776-2009 | | Oz/syd | Gsm |
| | | 7.5 | 255 |
| Shrinkage / Cambio dimensional (%) AATCC 135-2004 / IN504-15 | Lenght / Longitud | 5% | |
| | Trans / Transversal | 4% | |
| Spirality after laundry / Viraje despues del lavado (%) ISO16322-2-2005 | Lenght / Longitud | 3% | |
| | Trans / Transversal | | |
| Color fastness to wash / Solidez al lavado (gray scale) AATCC 61-2007 | Change / Cambio | 4 | |
| | Stain / Transf | 3 | |
| Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II AATCC 163-2007 | Stain / Transf | 4 | |
| Color fastness to light (gray scale) / Solidez a la luz BS 1006-1990 | Change / Cambio | 4 | |
| Color fastness to crocking (gray scale) / Solidez al frote AATCC 8-2007 | Dry / Seco | 4 | |
| | Wet / Húmedo | 3 | |
| Color Fastness to perspiration (gray scale) / Solidez a la transpiración AATCC 15-2007 | Change / Cambio | 4 | |
| | Stain / Transf | 3 | |
| Pilling / Pilling (Photographic) NTC 2051-2 / 2003 | | 3 | |
| Type of fabric / Tipo de tejido | | Knit | |

Tariff code white: 6004100000

Recommendations:

Rest for 20 to 24 hours before cutting.

Recommend testing before any treatment or application other than cutting and sewing.

